

Rec'd PCT/PTO 07 FEB 2005

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
19 February 2004 (19.02.2004)

PCT

(10) International Publication Number
WO 2004/015312 A1

(51) International Patent Classification⁷: **F16J 3/06**, F15B
15/10, B29C 53/58, B66F 3/35, E04H 15/20, F16F 9/04

van der Wieleweg 106, NL-2612 SZ Delft (NL). **BEUK-
ERS**, Adriaan [NL/NL]; A. Thijmlaan 17, NL-2106 EG
Heemstede (NL).

(21) International Application Number:
PCT/NL2002/000534

(74) Agent: **PRINS, A., W.**; Nieuwe Parklaan 97, NL-2587 BN
Den Haag (NL).

(22) International Filing Date: 8 August 2002 (08.08.2002)

(81) Designated States (*national*): AE, AG, AL, AM, AT (util-
ity model), AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA,
CH, CN, CO, CR, CU, CZ (utility model), CZ, DE (util-
ity model), DE, DK (utility model), DK, DM, DZ, EC, EE
(utility model), EE, ES, FI (utility model), FI, GB, GD, GE,
GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ,
LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN,
MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD,
SE, SG, SI, SK (utility model), SK, SL, TJ, TM, TN, TR,
TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(25) Filing Language: English

(26) Publication Language: English

(71) Applicant (*for all designated States except US*): **TECH-
NISCHE UNIVERSITEIT DELFT** [NL/NL]; Ju-
lianalaan 134, NL-2628 BL Delft (NL).


(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **KOUSSIOS**, Sotiris
[NL/NL]; Arthur van Schendelplein 45, NL-2624 CP Delft
(NL). **BERGSMA**, Otto, Korneles [NL/NL]; Stalpaert

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),

[Continued on next page]

(54) Title: **PRESSURIZABLE STRUCTURES COMPRISING DIFFERENT SURFACE SECTIONS**



(57) Abstract: The invention relates to composite pressurizable structures which are overwound with fibres or are braided. The pressurizable structures comprise axial sections which in turn comprise both concave and convex surfaces. The shape characteristics are related to geodesic as well as non-geodesic trajectories in regard of the fibres. Axial sections of the pressurizable structures can be rotated, expanded or bended with respect to the longitudinal axis of the pressurizable structure. Examples of uses of the pressurizable structure relate to pressure vessels and flexible pipelines, spring elements, robotic actuators and adaptable buildings. In another aspect, the invention relates to a method of production by means of braiding, which in principle allows for the construction of very large structures.

WO 2004/015312 A1

WO 2004/015312 A1

European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

Published:

— *with international search report*

WO 2004/015312

1

24/PRTS
10/523878
PCT/NL2002/000534
DT01 Rec'd PCT/EP 07 FEB 2005PRESSURIZABLE STRUCTURES COMPRISING DIFFERENT SURFACE SECTIONS

The invention relates to pressurizable structures comprising a gas- or fluid-tight body overwound with a number of fibre filaments, whereby the radius of the body varies along a rotation-symmetrical axis of the structure.

Pressurizable structures of the above-indicated type are well known in the art. A known pressurizable structure may comprise a body of which the radius varies with respect to a rotation-symmetrical axis of the structure, such that the body comprises a number of convex surface sections each having a local maximum radius, such as with isotensoidal or cylindrical bodies. When under internal pressure, such bodies form part of rigid, pressure-resistant structures.

It is an object of the invention to provide pressurizable structures of which the radius of the body varies with respect to a rotation-symmetrical axis of the structure, which structures when under pressure offer stiffness and strength of an order as that provided by known pressurizable structures of which the body comprises a number of convex surface sections.

It is another object of the invention to provide for pressurizable structures of the above-indicated type with a low requirement of material in regard of production and a large reduction in weight of the pressurizable structure.

Either or both objects are achieved by means of a fibre-reinforced pressurizable structure according to claim 1, which fibre-reinforced pressurizable structure comprises a gas- or fluid-tight body overwound with a number of fibre filaments, whereby the radius of the body varies with respect to a rotation-symmetrical axis of the structure, such that said body comprises a number of concave surface sections each having a local minimum radius, and a number of convex surface sections each having a local maximum radius, characterized in that at least one concave surface section is overwound with a fibre such that the longitudinal orientation of the fibre along a finite length thereof is orientated substantially perpendicular with respect to the rotation-symmetrical axis of the structure.

The advantage related to this technical element is that the pressurizable structure which comprises concave and convex surface sections is overwound with a fibre, such that at every locus on the surface of the structure, the fibre is under a constant tension, not only with respect to the convex surface sections but also with respect to concave surface sections of the pressurizable structure. In regard of the fibre, both geodesic trajectories (i.e. with zero friction between the fibre and the surface it lies on) as well as non-geodesic trajectories (non-zero friction between the fibre and the surface it lies on) are achievable.

WO 2004/015312

PCT/NL2002/000534

2

It is to be noted that the local orientation of the fibre on said concave surface section is intact and that it remains intact during use, even when the structure is not under internal pressure.

This basic concept makes it possible to connect bodies of pressurizable structures, which bodies comprise different surface sections, together by means of continuous overwinding, i.e. without the use of interconnecting means between bodies which are separately overwound. Large pressurizable structures comprising different axial sections, including axial sections having concave surfaces, are achievable whereby the fibre always follows a globular or bulbous trajectory as determined by the isotenoidal shape of the related axial section.

Preferably, the finite length of the fibre comprises a locus at which the fibre undergoes torsion with respect to its longitudinal centre-line. This is advantageous in that the transition between adjoining concave and convex surface sections can be achieved by means of a single fibre. More preferably, the finite length of the fibre comprises a locus at which there is reversal of the side of the fibre which is in contact with the body. This offers the advantage that transitions between adjoining axial sections having concave and convex surfaces whereby a transition occurs over a short length with respect to the rotational-symmetrical axis of the body may also be achieved by means of a single fibre.

Two further preferred embodiments in regard of this aspect of the invention are claimed according to claims 4 and 5.

According to another embodiment of the invention, the body of the fibre-reinforced pressurizable structure is flexible, i.e. non-rigid, and that the fibres are supported by a matrix material. This is advantageous in that large-scale structures may be constructed as comprising axial sections or substructures with different surfaces, whereby each axial section or substructure is separately foldable and inflatable/deflatable, such that the architecture and the local orientation of the fibre across the surface of the axial sections or substructures remain intact under all conditions of use.

Another advantage of this embodiment is that a part of the pressurizable structure according to the invention, at least an axial section thereof, can be brought into a working position whereby this section is not under internal pressure and thus its being in a compact state, and after being brought into its working position, the axial section being brought under internal pressure to its pressurized operating state. This provides for economical advantage and for access to and operability in tight spaces.

Embodiments comprising axial sections which can be positioned differently with respect to the rest of the pressurizable structure according to the invention, e.g. rotated, translated or bended with respect to the longitudinal axis of the pressurizable structure, are claimed

WO 2004/015312

PCT/NL2002/000534

3

in claims 7 to 9. Embodiments of the pressurizable structure according to the invention which are suitable for various applications are claimed in claims 11 to 15.

These and other aspects of the invention will be apparent from and elucidated with reference to the embodiment(s) described hereinafter.

5

Figure 1 depicts cross-sections of a number of isotenoidal profiles of the body of a pressurizable structure, to be seen in conjunction with Figure 4;

Figure 2 depicts graphically a pressurizable structure provided with a number of concave surface sections and a number of convex surface sections;

10 Figure 3 depicts a graphical representation of forces, surfaces, pressures and radii in light of definitions of the q-factor and r-factor;

Figure 4 depicts pressurizable structures having different ratios of the so-called q-factor, to be seen with reference to Figure 1;

15 Figure 5 depicts a graph of some relationships of the so-called r-factor to the geometry of the body of the pressurizable structure;

Figure 6 depicts schematically a reversal of the side of the fibre which is in contact with the body;

Figure 7 depicts schematically the occurrence of fibre twist and of reversal of the contact side of the fibre as functions of the q-factor and the r-factor;

20 Figure 8 depicts a graph of the dimensionless reduction of the pole opening for various μ -values as a function of the dimensionless equatorial radius;

Figure 9 depicts a graph of critical values of the dimensionless equatorial radius as a function of the applied friction;

25 Figure 10 depicts a graph of dimensionless values of displacement of the highest point of the structure as a function of the parameter ξ with different initial values of the r-factor;

Figure 11 depicts a graph of effective values of the r-factor as a function of the parameter ξ with different initial values of the r-factor;

Figure 12 depicts schematically translation and rotation of an axial section with respect to the longitudinal axis of the pressurizable structure;

30 Figure 13 depicts translation and bending of an axial section with respect to the longitudinal axis of the pressurizable structure;

Figure 14 depicts a hyperboloid axial section as an embodiment comprising an isotenoidal concave surface;

35 Figure 15 depicts schematically a correction moment as a reaction to inclination at a pole of the pressurizable structure;

WO 2004/015312

PCT/NL2002/000534

4

Figure 16 depicts graphically the deformed state of an axial section of the pressurizable structure resulting from inclination at the pole of the pressurizable structure;

Figure 17 depicts a graph of the correction moment which is generated as a function of angular deformation at the polar plane of the pressurizable structure;

5 Figure 18 depicts a graph of in-plane strains of an axial section when it is deformed into a flat surface;

Figure 19 depicts schematically a two-dimensional arrangement of pressurizable fuel tanks according to the invention;

10 Figure 20 depicts schematically a plan view of a combination of three pressurizable structures according to the invention;

Figures 21A, B and C depicts schematically the use of a pressurizable structure according to the invention as an elevator-driving element (21A), an excavator-driving element (21B) and a robotic actuator (21C), respectively;

15 Figure 22 depicts schematically a plan view of the ground floor of a pressurizable structure according to the invention which comprises means for a shoring or strutting function, such as construction beams;

Figure 23 depicts schematically an elevation of a building comprising pressurizable structures according to Figure 22; and

20 Figure 24 depicts schematically a step of a method for making a pressurizable structure according to Figure 22 by means of e.g. braiding.

With reference to Figure 1, almost every isotensoidal body is characterized by an infinite slope at its pole radius and its equator radius. A basic aspect of the invention is embodied in an oblong, quasi-cylindrical pressurizable structure which comprises alternatingly concave and convex surfaces of axial sections as shown in Figure 2. In regard of the surfaces, it should be noted that the fibre is under a constant tension at every locus of the surface.

25 The pressurizable structures according to the invention are conveniently defined in terms of the two parameters the q-factor and the r-factor. With reference to Figure 3, the q-factor is defined as the square of the dimensionless quotient of said local maximum radius of a convex surface section adjacent to the concave surface section in question and the local minimum radius of the concave surface section in question, and the r-factor is defined as the quotient of the total distribution of the axial load on the circumference of said local minimum radius and the internal axial force generated by the internal pressure on the surface of the axial section at said local maximum radius.

WO 2004/015312

PCT/NL2002/000534

5

Figure 4 depicts various combinations of vessels having different values of the q-factor and the r-factor, which combinations allow for different shapes.

The ratios of the q-factors and of the r-factors of adjoining axial sections of the pressurizable structure influence the shape of the applied meridian profile. In order to ensure smooth transition of the connecting fibre between the axial sections, r should not have a value smaller than $-1/q$; in this case, the maximum height (of what?) becomes equal to the height at the pole. The next important r-value is $r(z=0)$ where the height at the pole equalizes zero, see Figure 5.

Another important property in regard of the pressurizable structure according to the invention is that it allows for overwinding the same with a single fibre bundle. The latter is in contact with the surface throughout, both over convex as well as concave surface sections. Depending on the values of q and r, two different configurations can be followed in regard of the transition of the fibre from one axial section to an adjoining axial section of the structure, see Figure 6.

In cases whereby the q-factor and the r-factor of the body have values in the ranges of $q = \{1, 12\}$ and $r = \{-1/q, 0\}$, the winding angle at the pole (smallest radius) is approx. equal to $\pi/2$ [rad] and the degree of concavity is generally small, that is: i.e. the radius of normal curvature is large, so that the fibre is in contact with the concave surface section in question with its one and same side throughout and it undergoes a total twist equal to π [rad] over the length of the transition between two sections.

In cases whereby the q-factor and the r-factor of the body have values in the ranges of $q = \{1, 8\}$ and $r = \{-1/q, -1/(2q)\}$, or $q = \{8, \infty\}$ and $r = \{0, -1/q\}$, the winding angle at the pole remains equal to $\pi/2$ [rad] while the degree of concavity is generally very large, so that there is reversal of the side of the fibre which is in contact with the concave surface section. Both types of cases are depicted graphically in Figure 7.

Another important parameter in addition to the q-factor and the r-factor relates to the choice between geodesic- and non-geodesic trajectories of the fibre. A geodesic fibre path does not require any friction between the fibre and the surface its overwinds, while conversely a non-geodesic path for the fibre does require friction.

In regard of geodesic winding: assuming that there is zero friction ($\mu = 0$), then it is not possible to make an axial section which has different radii of the pole openings at its ends. This entails that one and the same meridional profile needs to be used for identical adjoining axial sections of the pressurizable structure. In addition, in case of the q-factor having small values, it leads to pole openings with considerable radii.

WO 2004/015312

PCT/NL2002/000534

6

In regard of non-geodesic winding: depending on the magnitude of μ and the chosen values of the q-factor and the r-factor, it allows for accommodation of the changing q-factor in regard of transition from one axial section to an adjoining section. The measure of decrease depends mainly on the dimensionless equator radius and μ , see Figure 8.

5 Having selected a particular value for μ , the radius of the pole opening may even become equal to zero with the value of the q-factor being sufficiently high. Figure 9 depicts values of the corresponding dimensionless equatorial radii.

10 Figures 8 and 9 thus relate to the case of achieving an isotenoidal shape by means of non-geodesic winding. It should be noted that the resulting meridian profile is significantly similar to the geodesic-isotenoidal one. This property allows for use in general of typical geodesic isotenoidal shapes notwithstanding the occurrence of friction. It should be noted that a particular q-value is directly coupled to the corresponding dimensionless equator radius.

15 The body of the pressurizable structure according to the invention can be either rigid or inflatable/deflatable. This distinction relates to the choice of use of matrix materials and in regard of the production process in terms of the desired quality, manufacturing time and required coefficient of friction between the fibre bundle and the surface which is to be overwound

20 In regard of a rigid pressurizable structure, its design procedure may be substantially similar to that of known isotenoidal pressurizable structures, either with or without implementation of friction. This is well known in the art, and hence rigid structures will not be described further in this patent application.

The following is a description of the aspect of variation of mechanical properties of the pressurizable structure according to the invention when it is under internal pressure.

25 The starting point is a column of pressurizable structures (which are isotenoidal of shape and are geodesically wound) with certain values of the q-factor, the r-factor and the internal pressure. In the event of deflation, the pressure reduction may be described by the parameter ξ which is equal to $P(\text{deflated})/P(\text{initial})$. The dimensionless value of displacement (=decrease in height) of the highest vessel point depends on the pressure reduction and the initial values of the q-factor and r-factor, see Figure 10.

30 Figure 10 represents the displacement-pressure modification curve for half of an axial section of a pressurizable structure. Depending on the number of interconnected axial sections, the curve in regard of the total pressurizable structure can be deduced on the basis of a series-connection of equivalent spring elements.

35 A modification of an axial section due to a change in its internal pressure corresponds in effect to a new value of its r-factor, with the proviso that the value of the q-factor also

WO 2004/015312

PCT/NL2002/000534

7

changes such that the total fibre length remains practically unchanged. An example of this modification of the r-factor as a result of a change in the internal pressure is shown in Figure 11.

Every initial $\{q,r\}$ configuration corresponds with distinctive values of minimum ξ and effective r-factor. The minimum ξ value is associated with a threshold value of the pressure which is required for countering the axial force at the top of the configuration of combined structures. The most important mechanical property of the pressurizable structure is the adaptability of the pressure-displacement characteristic thereof through variations in the values of the q-factor and/or of the r-factor as well as modification of the number of structures which are to be interconnected in parallel- or in series. Profiles on the basis of non-geodesic winding also provide an additional possibility for adapting the pressure-displacement characteristic of the pressurizable structure.

In addition to longitudinal displacements of one or more axial sections of the pressurizable structure, it can also be pivotable with respect to the longitudinal axis of the structure. In other words, one or more axial sections can also be subject to rotation with respect to the longitudinal axis of the structure. This can be achieved through modification of the fibre path, such that the total fibre length is greater than the geodesic length, see Figure 12. According to another possibility, such as in the case of a structure with an asymmetrical axial cross-section, at least one axial section of the structure is variable with respect to the longitudinal axis of the pressurizable structure. According to yet another possibility, an axial section of the structure is pivotable with respect to an axis, which axis is orthogonal with respect to the longitudinal axis of the pressurizable structure, see Figure 13.

During deflation the value of the effective r-factor becomes increasingly negative. When this value is smaller than $-1/q$, the vessel will behave slightly stiffer than as indicated by the predicted pressure-displacement characteristic (see Figure 10), due to extensive contact between adjoining axial sections of the pressurizable structure.

Figure 14 depicts the use of a hyperboloid axial section as an embodiment which can simultaneously be subject to both the axial length of the axial section being variable with respect to the longitudinal axis of the pressurizable structure (translation of the axial section) as well as this axial section being pivotable with respect to the longitudinal axis of the pressurizable structure (rotation of the axial section). The length of the fibre which overwinds this axial section remains constant throughout.

In regard of the stability of the pressurizable structure according to the invention, and with reference to Figure 15: when a deviation of the plane perpendicular to the longitudinal axis at an end plane of an axial section occurs, then the structure shall give rise to a moment

WO 2004/015312

PCT/NL2002/000534

8

which will counteract with respect to this deviation. The behavior of a pressurizable structure according to the invention can be derived from the stability of a single axial section. When it is in a deformed state, the pressurizable structure can be considered to be as a structure having a slightly modified distribution of the equator radius compared to a non-deformed state, with changes at the pole radius remaining substantially negligible, see Figure 16.

As a result of the deformation, the fibres will undergo different loads as a function of their angular position in the equatorial plane of the axial section. With reference to Figure 17, these loads will generate a moment tending to counter the deformation. The slope of the moment-angle curve depends on the design parameters $\{q,r\}$ and the applied fibre path (geodesic or non-geodesic). It is to be noted that the relationship between the deformation and the generated moment is linear.

The following is a description of the maximum stresses which arise in the event of deformation of a pressurizable structure according to the invention. Assume an initial situation of a structure comprising a stacked arrangement of axial sections. The maximum deformation imaginable is when the stacking of the structure is flattened to a state comparable to that of a stack of compact discs. In the flattened state, the axial sections have the same pole radius as in the initial state. As described above in relation to a hyperboloid structure, in order to maintain the same fibre length of a winding as in the initial state, the equator radius of the related axial section will have to increase. Consequently, the matrix should be able to withstand the generated stresses and strains. This analysis is based on the validity of a plane stress situation, whereby the fibres are considered to be infinitely stiff, e.g. as in Figure 18. When applying a typical rubber as the matrix material (e.g. Polyurethane), the maximum equivalent Hubert-Hencky stress remains below the yield value and occurs at the outer fibre locus (equator).

In regard of applicable pressure levels, these are theoretically unlimited, mainly depending on the applied fibre material and the number of windings. In practice, even when the strongest fibres are used, the physical volume of fibres practicable at the poles limits the number of windings. The latter sets a limit on the design pressure. Generally, pressure levels of e.g. 300 [bar] are achievable. This level forms a significant difference between a typical unreinforced inflatable structure and the pressurizable structure comprising combinations of axial sections according to the invention.

The pressurizable structure according to the invention can be used in various fields of technology. Some practical embodiments are pressure vessels which offer a comprehensible occupation of the available installation space at an optimum strength-to-weight ratio; adjustable springs; smart actuators serving as replacements for hydraulic or pneumatic cylinders; and robotic arms and elevators which can bear high loads and perform movements in multiple

WO 2004/015312

PCT/NL2002/000534

9

degrees of freedom. Other embodiments comprise pipelines such as flexible pipelines of which the dimensions and load-bearing properties are alterable. Also, large structures such as high-rise buildings comprising low-weight pressurizable axial sections according to the invention are feasible. An example relates to a vehicle-parking building which comprises a variable number of parking decks, whereby one or more decks comprise struts formed from pressurizable axial sections according to the invention and whereby a deck is taken into use by pressurizing the same only when so required. Yet further embodiments comprise smart structures such that when these are put to use as load-carrying members, the stiffness characteristics of the resulting structure can be adjusted, e.g. in the case of adaptation of the resonance frequencies of buildings during an earthquake or a blizzard).

With respect to the constraints of a given installation space, there are various possibilities of filling it with high-performance composite pressure vessels having considerable operating pressure levels. Such a use can be based on an arrangement according to Figure 19. A three-dimensional arrangement can advantageously increase the occupation of the space available. Another advantage of filling a space with an arrangement comprising several tanks is that in the event of a feed failure, there will still be enough fuel in the remaining pressurizable sections comprised in the arrangement to the end of keeping the related energy converter in operation. Such a fail-safe property is advantageous particularly in light of e.g. the aerospace industry.

In regard of the use of a pressurizable structure according to the invention as an adjustable spring; this can be achieved through a variation of the internal pressure of the axial sections of the structure in conjunction with use of its properties of adjustable values of its q-factor, r-factor and the choice of geodesic or non-geodesic trajectories of the fibre windings. Since high internal pressures are applicable, spring means with small dimensions can be implemented. With reference to Figure 20, an arrangement of axial sections linked together in parallel and at different loci is advantageous in regard of the performance of complicated movements whereby there are also considerable external loads exerted on the pressurizable structure.

In other uses involving e.g. hydraulic or pneumatic cylinders which are subject to considerable external loads, the functions of these cylinders can be implemented by means of an arrangement of pressurizable structures, as described above, which means also provide for the advantage of eliminating, or at least reducing, leaks and wear, the latter as a result of interaction between different moving mechanical parts. Considering that the pressure-displacement curve of said arrangement of pressurizable structures is readily adjustable, specific uses relate to elevators, excavators and heavy industrial robots, see Figure 21A-C.

WO 2004/015312

PCT/NL2002/000534

10

In regard of the use of a pressurizable structure according to the invention as a pipeline, the combination of a high pressure-bearing capability, of translational and rotational flexibility in addition to, theoretically, an infinite length of the pressurizable structure allows for the construction of continuous, adaptable pipelines. Depending on the required flexibility, the degrees of concavity and convexity are readily adjustable. The pipelines can be constructed on-site, or be transported in a compact, unpressurized state. The latter leads advantageously to a considerable reduction of the volume of the structure.

A further use of a pressurizable structure according to the invention relates to entitles such as struts or shoring means for buildings. Axial sections can be connected to each other by means of continuous overwinding to any desired length, even ad infinitum at least in principle, to form buildings. For example, consider a square building which comprises 10 floors. Consider further as a starting point that each floor is dimensioned to bear a floor load of 300 [kg/m²] and that it is shaped as a square of 10 [m] x 10 [m]. The required ceiling height of each floor is set to 3 [m]. At the ground floor, the maximum allowable radius of the pressurizable structure, which comprises a number of different axial sections, is set to be 1.25 [m]. Each of the four corners of the building is borne by one strut in the form of a pressurizable structure, see Figure 22. Calculations indicate that the required pressure at the ground floor is approx. 50 [bar]. If the pressurizable structure is to be continued through to the adjoining floor level, then the pressure of the adjoining axial section can be varied in accordance to the cumulative loads on all higher-lying floors. In situations in which a decrease of the equatorial radius to the maximum extent possible is required, a solution can be found through the use of smaller lengths of axial sections of which the pressurizable structure is comprised. Preferably, each floor should comprise an integer number of axial sections which extend exactly to the required ceiling height and which are in accordance with the pressure level required for the ground floor. The result of this analysis is depicted graphically in Figure 23.

If pressure valves are comprised between the different floors of the pressurizable structure according to the invention, then this offers the possibility of tailoring the pressure levels at each floor and it thus provides for an adjustable building. In practice, it would be preferable to construct each floor as being formed by a modular type of pressurizable structure, whereby the pressurizable structure in turn comprises a number of axial sections which are adjoined by means of overwinding. A modular type of pressurizable structure does not give rise to technical problems associated with the introduction of floor loads other than at an end of a pressurizable structure. The possibility of building floors formed by modular pressurizable structures allows for addition or removal of such floors, by which adjustable buildings can be made to be readily convertible for different functions, e.g. a factory hall being converted into a

WO 2004/015312

PCT/NL2002/000534

11

multi-deck parking garage. Further, the Eigen-frequencies of existing building structures, such as a steel framework of a building, can be made adaptable with respect to varying conditions, e.g. earthquakes and blizzards. Even further, a building can be built as follows. A pressurizable structure comprising a number of axial sections is put in place in its unpressurized state. The highest axial section is brought under internal pressure upto the desired floor load-bearing capacity. As required, e.g. a steel framework can be mounted onto the pressurized axial section. The adjoining axial section which is to form the underlying floor is then brought under internal pressure. Through repetition, each floor can be made at the ground level and raised. Such a method of constructing buildings leads advantageously to reduction of construction time and costs.

In another aspect, the invention relates to a method of producing pressurizable structures. Basically, the pressurizable structures according to the invention can be produced by means of filament winding and braiding. There are several possibilities which allow for choice of production speed and of the implementation of friction. For example, use can be made of winding or braiding with dry fibres, followed by application of matrix material by means of dimpling or spraying on to the fibres. Also, use can be made of winding or braiding with wet fibres, i.e. fibres which are impregnated with either a thermoplastic or a thermosetting matrix material. In the case of a pressurizable structure, if applicable, the matrix material should have deformation capabilities.

In any method of production, a body is required (mould or liner). The latter can remain in the structure after completion of the overwinding, as in the case of a rigid pressurizable structure which comprises several axial sections. In other cases, the body should be flexible in order to withstand the deformations of a pressurizable structure. Another possibility relates to the use of a removable liner in connection with a step of washing out, deflating or mechanically reducing its volume (such as with a so-called deployable liner). Filament winding is a well-known method of production, so only braiding will be described hereinafter in light of the possibility it offers for producing very long structures. With reference to Figure 24, consider the production of a strut for supporting a floor of a building. The ring shown in the Figure comprises the necessary number of independent fibre bundles required for overwinding the axial sections which are to be comprised in the pressurizable structure. The ring can undergo both a translational as well as a rotational movement. The fibres are to be drawn from a central arrangement of spools, whereby the central arrangement also translates and rotates with respect to the longitudinal axis of the pressurizable structure. Alternatively, the fibre spools themselves can be mounted on the ring itself. Overwinding can be continued from one axial section on to an adjoining axial section, with repetition hereof till

WO 2004/015312

PCT/NL2002/000534

12

completion of the pressurizable structure. In practice, there may be a limitation in regard of the total fibre length available on a spool. It should be noted that braiding can be implemented with an acceptable degree of accuracy only with the application of exclusively geodesic paths.

5 In regard of a transition between adjoining axial sections: depending on the r-factor, the fibre bundle undergoes a change of its contact side, see Figure 6. In this case, the method of braiding is easily implemented, because no additional spool rotations are required. In case of reversal of the side of the fibre which is in contact with the body, the fibre undergoes a twist whereby the spools mounted on the braiding ring have to rotate over the angle of twist with respect to the axis between the centre of gravity of the body and the centre of gravity of the
10 related spool. This is achievable by a proper construction of the spool attachments on the ring. A central spool arrangement will not work in such cases, other than in the case of braiding whereby the fibre bundle does not have to undergo a twist.

In regard of the width of the applied fibre bundle, in general a broad fibre will lead to less stacking of the fibre at the poles and to a reduction of braiding time. However, a broad
15 tape may make it difficult to achieve a winding geometry without any fibre interference at the transitional areas between adjoining axial sections. It should be noted that fibre interference does not occur if there is a twist in the fibre trajectory.

In regard of the choice between filament winding or braiding, it should be noted that. filament winding results in an accurate placement of each fibre over the axial sections (even in
20 the case of application of non-geodesic windings). It also leads to enhanced strength of the pressurizable structure since there is only one begin point and one endpoint of the applied fibre bundle. In the case of braiding, every applied winding will have its own begin point and endpoint, which in general results in a reduction of the strength of the pressurizable structure. A proper fixation of the fibre bundles in the pole area can alleviate any related problem.

25

WO 2004/015312

PCT/NL2002/000534

13

DEFINITIONS

- 5 **Isotensoidal shape** A rotationally symmetric shape designed in such a way that the applied fibres are tensioned in exactly the same magnitude.
- 10 **Dimensionless equatorial radius** The actual equatorial radius divided by the radius of the pole opening.
- 10 **Dimensionless pole opening radius** The minimum radius of the optimal part of the vessel divided by the radius of the pole opening (usually very close to 1).
- 15 **q-factor** The squared ratio of the dimensionless equatorial- and pole opening radius.
- 15 **r-factor** A dimensionless parameter describing the axial load on the pole opening as a fraction of the internal pressure load.
- 20 **$r(z=0)$** The critical value of r forcing the pole opening of a vessel to become on the same altitude as the equator.
- 25 **Geodesic trajectory** The path connecting two points on an arbitrary surface at the shortest possible way.
- 25 **Non-geodesic trajectory** A friction-requiring path connecting two points on an arbitrary surface.
- 30 **μ** The coefficient of friction between the fibre bundle and the surface of application.
- 35 **ξ** A dimensionless parameter expressing the pressure of a partially deflated vessel as a fraction of the original one.

WO 2004/015312

PCT/NL2002/000534

14

 ϵ_r

Radial strain in the plane of the vessel surface.

 ϵ_ϕ

Circumferential strain in the plane of the vessel surface.

5 $\gamma_{r\phi}$

Shear strain in the plane of the vessel surface.

10

WO 2004/015312

PCT/NL2002/000534

15

CLAIMS

1. Fibre-reinforced pressurizable structure comprising a gas- or fluid-tight body overwound with a number of fibre filaments, whereby the radius of the body varies with respect to a rotation-symmetrical axis of the structure, such that said body comprises a number of concave surface sections each having a local minimum radius, and a number of convex surface sections each having a local maximum radius, characterized in that at least one concave surface section is overwound with a fibre such that the longitudinal orientation of the fibre along a finite length thereof is orientated substantially perpendicular with respect to the rotation-symmetrical axis of the structure.
2. Fibre-reinforced pressurizable structure according to claim 1, characterized in that the finite length of the fibre comprises a locus at which the fibre undergoes torsion with respect to its longitudinal centre-line.
3. Fibre-reinforced pressurizable structure according to claim 1, characterized in that the finite length of the fibre comprises a locus at which there is reversal of the side of the fibre which is in contact with the body.
4. Fibre-reinforced pressurizable structure according to any of claims 1-3, whereby a parameter called the q-factor is defined as the square of the dimensionless quotient of said local maximum radius of a convex surface section adjacent to the concave surface section in question and the local minimum radius of the concave surface section in question, and whereby a dimensionless parameter called the r-factor is defined as the quotient of the total distribution of the external axial load on the circumference of said local minimum radius and the internal axial force generated by the internal pressure on the surface of the axial section at said local maximum radius, characterized in that when the q-factor and the r-factor of the body have values in the ranges of $q = \{1, 8\}$ and $r = \{-1/q, -1/(2q)\}$, or $q = \{8, \infty\}$ and $r = \{0, -1/q\}$, there is reversal of the side of the fibre which is in contact with the concave surface section.
5. Fibre-reinforced pressurizable structure according to any of claims 1-3, whereby a parameter called the q-factor is defined as the square of the dimensionless quotient of said local maximum radius of a convex surface section adjacent to the concave surface section in question and the local minimum radius of the concave surface section in question, and whereby a dimensionless parameter called the r-factor is defined as the quotient of the total distribu-

WO 2004/015312

PCT/NL2002/000534

16

tion of the external axial load on the circumference of said local minimum radius and the internal axial force generated by the internal pressure on the surface of the axial section at said local maximum radius, characterized in that when the q-factor and the r-factor of the body have values in the ranges of $q = \{1, 12\}$ and $r = \{-1/q, 0\}$, the fibre is in contact with the concave surface section in question with its one and same side throughout.

6. Fibre-reinforced pressurizable structure according to any of claims 1-5, characterized in that the body is flexible, i.e. non-rigid, and that the fibres are supported by a matrix material.

7. Fibre-reinforced pressurizable structure according to any of claims 1-6, characterized in that the axial length of at least one axial section of the structure is variable with respect to the longitudinal axis of the pressurizable structure.

8. Fibre-reinforced pressurizable structure according to any of claims 1-6, characterized in that at least one axial section of the structure is pivotable with respect to the longitudinal axis of the pressurizable structure.

9. Fibre-reinforced pressurizable structure according to any of claims 1-6, characterized in that at least one axial section of the structure is pivotable with respect to an axis, which axis is orthogonal with respect to the longitudinal axis of the pressurizable structure.

10. Fibre-reinforced pressurizable structure according to any of claims 7-9, characterized in that at least one axial section of the structure comprises a combination of at least two of the technical elements of said claims, e.g. in that at least one axial section of the structure is pivotable with respect to the longitudinal axis of the pressurizable structure and that the axial length of this axial section of the structure is variable with respect to the longitudinal axis of the pressurizable structure as in the case in which the pressurizable structure comprises a substantially hyperboloid shape.

11. Fibre-reinforced pressurizable structure according to any of claims 1-10, characterized in that the pressurizable structure comprises a one- to three dimensional arrangement of a number of pressurizable fuel tanks or pipelines.

WO 2004/015312

PCT/NL2002/000534

17

12.Fibre-reinforced pressurizable structure according to any of claims 1-11, characterized in that the pressurizable structure comprises a spring means for a load-displacement function, preferably an adjustable load-displacement function.

5 13.Fibre-reinforced pressurizable structure according to any of claims 1-11, characterized in that the pressurizable structure comprises means for an actuating function, such as for elevators, excavators and industrial robots.

10 14.Fibre-reinforced pressurizable structure according to any of claims 1-11, characterized in that the pressurizable structure comprises means for a shoring or strutting function, such as construction beams.

15 15.Fibre-reinforced pressurizable structure according to claim 14, characterized in that the means for a shoring or strutting function, such as construction beams, are adaptable to the Eigen-frequencies of the pressurizable structure.

- 0 - 0 - 0 -

WO 2004/015312

PCT/NL2002/000534

1/24




Fig. 1

WO 2004/015312

PCT/NL2002/000534

2/24




Fig. 2

WO 2004/015312

PCT/NL2002/000534

3/24




Fig. 3

WO 2004/015312

PCT/NL2002/000534

4/24




Fig. 4

WO 2004/015312

PCT/NL2002/000534

5/24




Fig. 5

WO 2004/015312

PCT/NL2002/000534

6/24




Fig. 6

WO 2004/015312

PCT/NL2002/000534

7/24




Fig. 7

WO 2004/015312

PCT/NL2002/000534

8/24




Fig. 8

WO 2004/015312

PCT/NL2002/000534

Critical equator radius as a result of friction




Fig. 9

WO 2004/015312

PCT/NL2002/000534

10/24




Fig.10

WO 2004/015312

PCT/NL2002/000534

11/24




Fig. 11

WO 2004/015312

PCT/NL2002/000534

12/24




Fig. 12

WO 2004/015312

PCT/NL2002/000534

13/24




Fig. 13

WO 2004/015312

PCT/NL2002/000534

14/24




Fig. 14

WO 2004/015312

PCT/NL2002/000534

15/24




Fig.15

WO 2004/015312

PCT/NL2002/000534

16/24




Fig. 16

WO 2004/015312

PCT/NL2002/000534

17/24




Fig. 17

WO 2004/015312

PCT/NL2002/000534

18/24




Fig. 18

WO 2004/015312

PCT/NL2002/000534

19/24




Fig. 19

WO 2004/015312

PCT/NL2002/000534

20/24




Fig. 20

WO 2004/015312

PCT/NL2002/000534

21/24




Fig. 21 C




Fig. 21 B




Fig. 21 A

WO 2004/015312

PCT/NL2002/000534

22/24




Fig. 22

WO 2004/015312

PCT/NL2002/000534

23/24




Fig. 23

WO 2004/015312

PCT/NL2002/000534

24/24




Fig. 24

INTERNATIONAL SEARCH REPORT

 International Application No
 PCT/NL 02/00534

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 F16J3/06 F15B15/10 //B29C53/58,B66F3/35,E04H15/20,F16F9/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B29C B66F E04H F15B F16F F16J F17B F17C F17D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 777 868 A (LARSSON OVE) 18 October 1988 (1988-10-18) column 1, line 1 - line 35 column 3, line 19 - line 28; figures 2,5	1,6-10
X	US 5 385 262 A (COQUET PASCAL D ET AL) 31 January 1995 (1995-01-31) column 1, line 1 - line 12 column 2, line 45 - line 57 column 3, line 50 - line 61; figures 1,2	1,3,11
X	EP 0 626 338 A (ZUMRO B V) 30 November 1994 (1994-11-30) page 1, line 1 - line 3	1,6,7, 11,13
Y	page 4, line 51 - line 58 page 5, line 19 - line 25; figures 8,10,11 -/-	2,12,14, 15

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

Z document member of the same patent family

Date of the actual completion of the international search

17 April 2003

Date of mailing of the international search report

06/05/2003

Name and mailing address of the ISA

 European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl
 Fax: (+31-70) 340-3016

Authorized officer

Ingelgard, T.

INTERNATIONAL SEARCH REPORT

In (ional) Application No
PCT/NL 02/00534

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 4 440 587 A (THOMPSON RICHARD J ET AL) 3 April 1984 (1984-04-03) column 1, line 1 - line 30; figure 1	2
Y	US 3 321 200 A (MING-CHIH YEW ET AL) 23 May 1967 (1967-05-23) column 1, line 1 - line 29; claim 4; figure 2	12
Y	WD 94 12423 A (KROEPLIN BERND ;TALMANN TORSTEN (DE)) 9 June 1994 (1994-06-09) page 30, paragraph 4 -page 31, paragraph 1; claims 1,7; figure 11	14,15
A	GB 1 064 590 A (AEROJET GENERAL CO) 5 April 1967 (1967-04-05) page 4, line 11 - line 41; claims 1,6	2

International Application No. PCT/NL 02 00534

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

Continuation of Box I.2

Claims Nos.: 3,4

The parameters used in claim 3 and 4 to define the geometry of the pressurizable structure makes a meaningful comparison with the prior art impossible.

The applicant's attention is drawn to the fact that claims, or parts of claims, relating to inventions in respect of which no international search report has been established need not be the subject of an international preliminary examination (Rule 66.1(e) PCT). The applicant is advised that the EPO policy when acting as an International Preliminary Examining Authority is normally not to carry out a preliminary examination on matter which has not been searched. This is the case irrespective of whether or not the claims are amended following receipt of the search report or during any Chapter II procedure.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/NL 02/00534**Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)**

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☒ Claims Nos.: 3, 4
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
see FURTHER INFORMATION sheet PCT/ISA/210
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this International application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/NL 02/00534

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4777868	A	18-10-1988	SE 453860 B AT 44405 T DE 3571343 D1 EP 0244409 A1 FI 872709 A JP 62501723 T SE 8406404 A WO 8603816 A1	07-03-1988 15-07-1989 10-08-1989 11-11-1987 17-06-1987 09-07-1987 18-06-1986 03-07-1986
US 5385262	A	31-01-1995	FR 2694066 A1 AU 4213993 A CA 2100981 A1 DE 69311013 D1 DE 69311013 T2 EP 0580535 A1 ES 2104107 T3 JP 6213398 A NO 932648 A ,B, NZ 248216 A	28-01-1994 27-01-1994 24-01-1994 03-07-1997 08-01-1998 26-01-1994 01-10-1997 02-08-1994 24-01-1994 28-03-1995
EP 0626338	A	30-11-1994	EP 0626338 A1 GR 3030309 T3 AT 177721 T AU 677306 B2 AU 6320794 A CA 2124309 A1 DE 69417101 D1 DE 69417101 T2 DK 626338 T3 ES 2131629 T3 JP 7002494 A ZA 9403642 A	30-11-1994 30-09-1999 15-04-1999 17-04-1997 01-12-1994 27-11-1994 22-04-1999 28-10-1999 11-10-1999 01-08-1999 06-01-1995 24-01-1995
US 4440587	A	03-04-1984	NONE	
US 3321200	A	23-05-1967	NONE	
WO 9412423	A	09-06-1994	AT 171442 T AU 5563094 A CA 2149908 A1 DE 4339211 A1 DE 59309016 D1 WO 9412423 A1 EP 0674597 A1 ZA 9308614 A	15-10-1998 22-06-1994 09-06-1994 26-05-1994 29-10-1998 09-06-1994 04-10-1995 18-05-1995
GB 1064590	A	05-04-1967	BE 656471 A FR 1414309 A NL 6413414 A	16-03-1965 15-10-1965 20-05-1966